

Specification Cross Reference

U.S. ALLOY	FRENCH AFNOR	GERMAN DIN	UK B.S.	JAPAN JIS	SWEDEN SS
304	Z 6CN18.09	1.4301	304 S 15	SUS 304	2333
304L	Z 2CN18.10	1.4306	304 S 11	SUS 304L	2352
310S	Z 8CN25.20	1.4845	310 S 16	SUS 310S	2361
316	Z 6CND17.11	1.4401	316 S 31	SUS 316	2343
		1.4436	316 S 33		2347
316L	Z 2CND17.12	1.4435	316 S 11	SUS 316L	2353
			316 S 13		2348
317		1.4436	317 S 16	SUS 317	2366
317L	Z 2CND19.15	1.4435	317 S 12	SUS 317L	2367
321	Z 6CNT18.10	1.4541	321 S 31	SUS 321	2337
347	Z 6CNNb18.10	1.455	347 S 17	SUS 347	2338